

## Alloy: C95510HT

**Bronze Family:** Nickel Aluminum Bronze

**Solids:** 1/2" to 9" OD

**Tubes:** 1-1/8" to 9" OD

**Rectangles:** Up to 15"

**Standard Lengths:** 24" Maximum Length

## Typical Uses

**Aerospace** Landing Gear Bushings & Bearings, Valve Guides, Stems and Seats

**Industrial** Corrosion Resistant Parts, Wear Rings,  
Machine Tool Parts, Piston Guides, Worm Wheels

**Marine** Propeller Hubs, Wear Rings, Hardware, Worm Gears, Shafts, Sleeves

## Condition

Quench hardened and temper annealed (TQ50)

## Similar or Equivalent Specification

CDA	ASTM	ASARCON	SAE	AMS	FEDERAL	INGOT	MILITARY	OTHER
			AMS 4880	4880				

## Chemical Composition

Alloy	Cu%	Sn%	Pb%	Zn%	Fe%	Ni%	Sb%	P%	S%	Al%	Mn%	Si%
C95510HT	78.00	0.2	N/A	0.3	2.0- 3.5	4.5- 5.5	N/A	N/A	N/A	9.7- 10.9	1.5	N/A

**Note:** Single values represent maximums.

## Mechanical Properties

	Tensile Strength, min	Yield Strength, at 0.2% offset	Elongation in 4D	Hardness
Castings 4.0 and under	105.0 ksi	62.5 ksi	9%	HB 3000 KG 192 to 248
Castings 4.0 and over	95.0 ksi	56.0 ksi	9%	HB 3000 KG 192 to 248

Mechanical Properties according to SAE

## Physical Properties (Based on C95500)

Melting Point - Liquidus	1930 F
Melting Point - Solidus	1900 F
Density	0.272 lb/in <sup>3</sup> at 68 F
Specific Gravity	7.530
Electrical Resistivity	122.80 ohms-cmil/ft @ 68 F
Electrical Conductivity	8 %IACS @ 68 F
Thermal Conductivity	24.20 Btu · ft/(hr · ft <sup>2</sup> ·oF)at 68F
Coefficient of Thermal Expansion	9 ·10 <sup>-6</sup> per oF (68-572 F)
Specific Heat Capacity	0.10 Btu/lb/oF at 68 F
Modulus of Elasticity in Tension	16000 ksi
Magnetic Permeability	1.20
Machinability Rating	50

For more information contact Dura-Bar Metal Services

2195 W. Lake Shore Drive, Woodstock, IL | 770 Cedar Springs Road, Salisbury, NC | 90 Grumbacher Road, York, Pa | 2320 Pecan Court, Fort Worth, Tx  
888-387-2227 | [dura-barms.com](http://dura-barms.com)